



POLYBUTADIENE COMPOSITION

RECEIVED

SEP 11 2001

TC 1700

Background of the Invention

The present invention relates to a polybutadiene
5 composition. More particularly, it relates to a polybutadiene
composition in which the thermal degradation under an air free
environment is prevented.

Polybutadiene type polymers having butadiene units as
their polymerization unit have been widely used as various
10 molded articles, since they exhibit same strength and elastic
property as vulcanized elastomers and same thermo plastic
property as thermoplastic resins. However, polybutadiene
type polymers are apt to deteriorate by heat and to generate
cross-linked products (gelled product) under heating. Such
15 cross-linked products cause bad appearance of the molded
article obtained by molding the polybutadiene type polymer.
Particularly, when the molded article is a film, the
cross-linked products lower the strength of the article.


For preventing such thermal degradation, a polybutadiene
20 composition comprising a polybutadiene type polymer and an
antioxidant is proposed. (JP-A-1-182308, etc.)

However, thermal degradation of such a conventional
polybutadiene composition is not sufficiently prevented when
the composition is heated under an air-free environment such
25 as the inner part of an extruder.

The present inventors have conducted extensive studies
to develop a polybutadiene composition which does not
deteriorate by heating even under an air-free environment.

As a result, they have found that a polybutadiene composition comprising a specific compound does not deteriorate by heating even under an air-free environment. Thus, the present invention was completed.

5 The present invention provides a polybutadiene composition comprising a polybutadiene type polymer and a compound represented by the following formula (I):



10

wherein Ar^1 and Ar^2 each independently represent an aromatic ring, X and Y each independently represent an alkylene group having one or two carbon atoms, an oxygen atom or a carbonyl group. (Hereinafter, this compound is referred to as

15 "Compound (I)".)

The polybutadiene type polymer comprised in a polybutadiene composition of the present invention is a polymer having a polymerization unit derived from butadiene. Examples of the polybutadiene type polymers include polybutadiene, styrene-butadiene copolymers, acrylonitrile-butadiene copolymers, acrylonitrile-butadiene-styrene copolymers, styrene-butadiene block copolymers, and impact resistant polystyrenes. The polybutadiene type polymer may be either a rubber or a resin. Polybutadiene may be either a

20

25 polybutadiene rubber produced by a solution polymerization or a polybutadiene rubber produced by a emulsion polymerization.

The impact resistant polystyrene is a polystyrene modified with a polybutadiene rubber, a styrene-butadiene copolymer rubber or the like to suppress occurrence of cracks caused by an impact. Such polybutadiene type polymers can be produced, for example, by a solution polymerization method, emulsion polymerization method, decomposition of polymer, or the like. The polybutadiene type polymer may be used alone or as a mixture of two or more.

Examples of the aromatic ring represented by Ar^1 or Ar^2 in the formula (I) include a benzene ring and naphthalene ring.

X and Y in the formula (I) are divalent residues. X and Y, which are same to or different from each other, represent an alkylene group having one or two carbon atoms, an oxygen atom or a carbonyl group. The alkylene group having one or two carbon atoms may be, for example, a methylene group, dimethylene group. The alkylene group may also be a substituted alkylene group, where the hydrogen atom is substituted with another atom or a group. It is preferred that at least one of X and Y is an alkylene group having one or two carbon atoms, and it is more preferred that both of X and Y are alkylene groups having one or two carbon atoms.

Each of X or Y bonds to a carbon atom in Ar^1 in the formula (I), and a carbon atom in Ar^2 in the formula (I). The two carbon atoms in Ar^1 or Ar^2 bonding to X or Y are usually adjacent to each other.

The aromatic ring represented by Ar^1 or Ar^2 may be substituted with one or more substituents. Examples of the substituents include an alkyl group, a cycloalkyl group, an

aryl group, an aralkyl group, an alkoxy group, an acyloxy, a hydroxyl group, a halogen atom, a sulfonyl group and a carbonyl group.

Examples of the alkyl group as the substituent on Ar¹ or Ar² include methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, t-butyl, 2-ethylbutyl, n-pentyl, isopentyl, 1-methylpentyl, 1,3-dimethylbutyl, n-hexyl, 1-methylhexyl, n-heptyl, 1-methylheptyl, 3-methylheptyl, n-octyl, t-octyl, 2-ethylhexyl, 1,1,3-trimethylhexyl, 1,1,3,3-tetramethylpentyl, nonyl, decyl, undecyl, 1-methyundecyl, dodecyl, 1,3,3,5,5-hexamethylhexyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, eicosyl and docosyl.

Preferably, the alkyl group is an alkyl group having one to 6 carbon atoms. The hydrogen atom(s) therein may be optionally substituted with another atom or a group.

As the cycloalkyl group as the substituent on Ar¹ or Ar², a cycloalkyl group having 5 to 8 carbon atoms can be exemplified. Specific examples thereof include cyclopentyl, methylcyclopentyl, dimethylcyclopentyl, cyclohexyl, methylcyclohexyl, dimethylcyclohexyl, trimethylcyclohexyl, t-butylcyclohexyl, cycloheptyl and cyclooctyl. The hydrogen atom in such a cycloalkyl group may be optionally substituted with another atom or a group.

As the aryl group as the substituent on Ar¹ or Ar², an aryl group having 6 to 20 carbon atoms can be exemplified. Specific examples thereof include phenyl, o-tolyl, p-tolyl, 2,3-xylyl, 2,4-xylyl, 2,5-xylyl, mesityl, naphthyl and

anthryl. The hydrogen atom in such an aryl group may be optionally substituted with another atom or a group.

As the aralkyl group as the substituent on Ar¹ or Ar², an aralkyl group having 7 to 20 carbon atoms can be exemplified.


5 Specific examples thereof include benzyl, phenylmethyl, methylbenzyl and naphthyl methyl. The hydrogen atom in such an aralkyl group may be optionally substituted with another atom or a group.

As the alkoxyl group as the substituent on Ar¹ or Ar²,
10 an alkoxyl group having 1 to 18 carbon atoms can be exemplified. Specific examples thereof include methoxy, ethoxy, n-propoxy, isopropoxy, n-butoxy, isobutoxy, sec-butoxy, pentyloxy and octadecyloxy. The hydrogen atom in such an alkoxyl group may be optionally substituted with another atom or a group.

15 As the acyloxyl group as the substituent on Ar¹ or Ar², an acyloxyl group having 1 to 18 carbon atoms can be exemplified. Specific examples thereof include acetoxy, propionyloxy, butyryloxy, isobutyryloxy, valeryloxy, isovaleryloxy and stearyloxy. The hydrogen atom in such an acyloxyl group may
20 be optionally substituted with another atom or a group.

As the halogen atom as the substituent on Ar¹ or Ar², a fluorine atom, a chlorine atom and a bromine atom can be exemplified.

When Ar¹ and Ar² are benzene rings, the compound
25 represented by the formula (I) is a compound represented by the following formula (I-1):



wherein m and n each independently represent an integer of 0 - 4, R represent an alkyl group, a cycloalkyl group, an aryl group, an aralkyl group, an alkoxyl group, an acyloxy group, a hydroxyl group, a halogen atom, a sulfonyl group and a carbonyl group, provided that, when sum of m and n is two or more, the groups of R may be same to or different from each other.

Examples of the compounds represented by the formula

(I) include:

xanthene,

2,7-dimethylxanthene,

3,6-dimethylxanthene,

4,5-dimethylxanthene,

1,8-dimethyl-4,5-diisopropylxanthene,

9-phenylxanthene,

2-benzylxanthene,

9-benzylxanthene,

9-p-torylxanthene,

2,7-dimethyl-9-phenylxanthene,

9-hydroxylxanthene,

9-carboxylxanthene,

9-methoxycarbonylxanthene,

9-methyl-9H-xanthene-2,7-diol,

9-ethyl-9H-xanthene-2,7-diol,

- 9-isopropyl-9H-xanthene-2,7-diol,
- 9-phenyl-9H-xanthene-2,7-diol,
- 3,4,5,6-tetramethyl-9H-xanthene-2,7-diol,
- 3,4,5,6,9-pentamethyl-9H-xanthene-2,7-diol,
- 5 3,4,5,6-tetramethyl-9-ethyl-9H-xanthene-2,7-diol,
- 1,3,4,5,6,8-hexamethyl-9H-xanthene-2,7-diol,
- 3,6-di-t-butyl-9-methyl-9H-xanthene-2,7-diol,
- 3,6-di-t-butyl-9-ethyl-9H-xanthene-2,7-diol,
- 3,6-di-t-butyl-9-cyclohexyl-9H-xanthene-2,7-diol,
- 10 1,3,4,5,6,8,9-heptamethyl-9H-xanthene-2,7-diol,
- 1,3,4,5,6,8-hexamethyl-9-ethyl-9H-xanthene-2,7-diol,
- 1,3,4,5,6,8-hexamethyl-9-isopropyl-9H-xanthene-2,7-diol,
- 1,3,4,5,6,8-hexamethyl-9-phenyl-9H-xanthene-2,7-diol,
- xanthone,
- 15 1-hydroxyxanthone,
- 2-hydroxyxanthone,
- 3-hydroxyxanthone,
- 4-hydroxyxanthone,
- 1,3-dihydroxyxanthone,
- 20 1,3-dihydroxy-7-methoxyxanthone,
- 1,6,8-trihydroxy-3-methylxanthone,
- 1,3,6,7-tetrahydroxyxanthone,
- 2-chloroxanthone,
- 1,2-benzxanthone,
- 25 2,3-benzxanthone,
- 1,8-diisopropenylxanthone,
- anthraquinone,
- 1-hydroxyanthraquinone,

1-methylanthraquinone,
2-methylanthraquinone,
2-ethylanthraquinone,
2-propylanthraquinone,
5 2-isopropylanthraquinone,
2-t-butylanthraquinone,
2-t-amylanthraquinone,
1,2-benzanthraquinone,
2-hydroxyanthraquinone,
10 1,2-dimethylanthraquinone,
1,3-dimethylanthraquinone,
1,4-dimethylanthraquinone,
2,3-dimethylanthraquinone,
2,6-dimethylanthraquinone,
15 1,3-diethylanthraquinone,
1,2,4-trimethylanthraquinone,
1,3,6-trimethylanthraquinone,
1,4,6-trimethylanthraquinone,
1,3,5,7-tetramethylanthraquinone,
20 1,3,6,8-tetramethylanthraquinone,
anthraquinone-1-sulfonic acid,
anthraquinone-2-sulfonic acid,
sodium anthraquinone-1-sulfonate,
sodium anthraquinone-2-sulfonate,
25 anthraquinone-1,5-disulfonic acid,
anthraquinone-1,8-disulfonic acid,
anthraquinone-2,6-disulfonic acid,
anthraquinone-2,7-disulfonic acid,

anthraquinone-1,6-disulfonic acid,
anthraquinone-1,7-disulfonic acid,
2-methylanthraquinone-1-sulfonic acid,
2-ethylanthraquinone-1-sulfonic acid,
5 2,6-dimethylanthraquinone-1-sulfonic acid,
1,2-dihydroxyanthraquinone,
1,3-dihydroxyanthraquinone,
1,4-dihydroxyanthraquinone,
1,5-dihydroxyanthraquinone,
10 1,6-dihydroxyanthraquinone,
1,7-dihydroxyanthraquinone,
1,8-dihydroxyanthraquinone,
2,3-dihydroxyanthraquinone,
2,6-dihydroxyanthraquinone,
15 2,7-dihydroxyanthraquinone,
1,2,3-trihydroxyanthraquinone,
1,2,4-trihydroxyanthraquinone,
1,2,5-trihydroxyanthraquinone,
1,2,6-trihydroxyanthraquinone,
20 1,2,7-trihydroxyanthraquinone,
1,2,8-trihydroxyanthraquinone,
1,4,6-trihydroxyanthraquinone,
1,2,3,4-tetrahydroxyanthraquinone,
1,2,4,6-tetrahydroxyanthraquinone,
25 1,2,5,6-tetrahydroxyanthraquinone,
1,2,5,8-tetrahydroxyanthraquinone,
1,2,6,7-tetrahydroxyanthraquinone,
1,2,7,8-tetrahydroxyanthraquinone,

- 1,3,5,7-tetrahydroxyanthraquinone,
1,4,5,8-tetrahydroxyanthraquinone,
1,2,3,5,7-pentahydroxyanthraquinone,
1,2,4,5,8-pentahydroxyanthraquinone,
5 1,2,3,5,6,7-hexahydroxyanthraquinone,
1,2,4,5,6,8-hexahydroxyanthraquinone,
1,2,4,5,7,8-hexahydroxyanthraquinone,
1-methoxyanthraquinone,
2-methoxyanthraquinone,
10 1,3-dimethoxyanthraquinone,
1,4-dimethoxyanthraquinone,
1-ethoxyanthraquinone,
1,2-dihydroxyanthraquinone-3-sulfonic acid,
1,2,4-trihydroxyanthraquinone-3-sulfonic acid,
15 2,7-dihydroxyanthraquinone-3,6-disulfonic acid,
1,5-dihydroxyanthraquinone-2,6-disulfonic acid,
1,8-dihydroxyanthraquinone-2,7-disulfonic acid,
1,2-dihydroxyanthraquinone-3,8-disulfonic acid,
1-chloroanthraquinone,
20 1,2-dichloroanthraquinone,
1,3-dichloroanthraquinone,
1,4-dichloroanthraquinone,
1,5-dichloroanthraquinone,
1,6-dichloroanthraquinone,
25 1,7-dichloroanthraquinone,
1,8-dichloroanthraquinone,
2,3-dichloroanthraquinone,
2,6-dichloroanthraquinone,

2,7-dichloroanthraquinone,
 1,2,4-trichloroanthraquinone,
 1,4,5-trichloroanthraquinone,
 1,4,6-trichloroanthraquinone;
 5 1,2,3,4-tetrachloroanthraquinone,
 1,4,5,8-tetrachloroanthraquinone,
 1-bromoanthraquinone,
 2-bromoanthraquinone,
 1,2-dibromoanthraquinone,
 10 1,3-dibromoanthraquinone,
 1,4-dibromoanthraquinone,
 1,5-dibromoanthraquinone,
 1,6-dibromoanthraquinone,
 1,7-dibromoanthraquinone,
 15 1,8-dibromoanthraquinone,
 2,3-dibromoanthraquinone,
 2,6-dibromoanthraquinone,
 2,7-dibromoanthraquinone,
 1-chloro-4-methylanthraquinone,
 20 1-chloro-2-methoxylantraquinone,
 1-methoxy-4-methylanthraquinone,
 1-chloro-4-hydroxylantraquinone,
 1-hydroxyl-2,4-dibromoanthraquinone,
 1,3,5,7-tetrahydroxyl-2,6-dibromoanthraquinone,
 25 2,3-benzanthraquinone,
 anthrone,
 1-methylanthrone,
 2-methylanthrone,

3-methylanthrone,
10-methylanthrone,
10-ethylanthrone,
1,3-dimethylanthrone,
5 1,4-dimethylanthrone,
2,3-dimethylanthrone,
2,4-dimethylanthrone,
2,6-dimethylanthrone,
2-phenylanthrone,
10 10-phenylanthrone,
10-benzylanthrone,
2-chloroanthrone,
10-chloroanthrone,
1,6-dichloroanthrone,
15 4,10-dichloroanthrone,
10-bromoanthrone,
1-methoxyanthrone,
1-acetoxyanthrone,
10-acetoxyanthrone,
20 1-hydroxyanthrone,
2-hydroxyanthrone,
10-carboxyanthrone,
1-chloro-10-phenylanthrone,
1,5-dichloro-10-phenylanthrone,
25 10,10-bianthranyl,
1-chloroanthrone,
2,6-dichloroanthrone,
1,2-benzanthrone,

1-hydroxy-2-chloro-4,5-benzanthrone,
 9,10-dihydroanthracene,
 sodium 9,10-dihydroanthracene sulfonate,
 9,10-dihydroanthroryl methyl triethylammonium chloride,
 5 9,10-dihydro-1-methylanthracene,
 9,10-dihydro-2-methylanthracene,
 9,10-dihydro-2-ethylanthracene,
 1-(1,1-dimethylethyl)-9,10-dihydroanthracene,
 9,10-dihydro-2-phenylanthracene,
 10 9,10-dihydro-1-(phenylmethyl)-anthracene,
 9,10-dihydro-2-(phenylmethyl)-anthracene,
 9,10-dihydro-1-(chloromethyl)-anthracene,
 9,10-dihydro-1-anthracenemethanol,
 1-cyclohexyl-9,10-dihydroanthracene,
 15 9,10-dihydro-2-methoxylantracene,
 9,10-dihydro-1-anthracene carboxylic acid,
 9,10-dihydro-2-anthracene carboxylic acid,
 1-fluoro-9,10-dihydroanthracene,
 2-fluoro-9,10-dihydroanthracene,
 20 1-chloro-9,10-dihydroanthracene,
 2-chloro-9,10-dihydroanthracene,
 9,10-dihydro-1,4-dimethylanthracene,
 9,10-dihydro-2,6-dimethylanthracene,
 9,10-dihydro-2,7-dimethylanthracene,
 25 2,6-bis(1,1-dimethylethyl)-9,10-dihydroanthracene,
 2,7-bis(1,1-dimethylethyl)-9,10-dihydroanthracene,
 9,10-dihydro-1,4-dimethoxylantracene,
 9,10-dihydro-1,5-dimethoxylantracene,

- 9,10-dihydro-2,6-dimethoxylantracene,
 9,10-dihydro-2,7-dimethoxylantracene,
 9,10-dihydro-1,8-dimethoxylantracene,
 9,10-dihydro-1,5-diethoxylantracene,
 5 9,10-dihydro-1,8-diethoxylantracene,
 9,10-dihydro-1-ethoxy-8-methoxy-lanthracene,
 8-chloro-9,10-dihydro-1-anthracene carboxylic acid,
 9,10-dihydro-1,8-dimethoxy-anthracene carboxylic acid,
 9,10-dihydro-1,4-anthracenediol,
 10 9,10-dihydro-1,8-anthracenediol,
 9,10-dihydro-2,6-anthracene dicarboxylic acid,
 5-chloro-9,10-dihydroanthracene,
 2,6-dichloro-9,10-dihydroanthracene,
 9,10-dihydro-2,3,6,7-tetramethylantracene,
 15 9,10-dihydro-2,3,7,8-anthracene tetraol tetra acetic acid,
 9,10-dihydro-1,2,5,6-anthracene tetraol,
 9,10-dihydro-2,3,6,7-tetramethoxyanthracene,
 9,10-dihydro-2,3,6,7-tetraethoxyanthracene,
 1,2,3,4-tetrachloro-9,10-dihydroanthracene,
 20 1,4,5,6-tetrafluoro-9,10-dihydroanthracene,
 9,10-dihydro-1,2,3,4,5,6,7,8-octamethylantracene,
 9,10-dihydro-2,9'-bianthracene,
 9,10-dihydro-2,7-anthracene dicarboxylic acid dimethyl
 ester,
 25 10,11-dihydro-5H-dibenzo[a,d]cycloheptene,
 1,9-dibromo-3,7-bis(1,1-dimethylethyl)-10,11-dihydro-5H-d
 ibenzo[a,d]cycloheptene,
 3,3'-(10,11-dihydro-5H-dibenzo[a,d]cycloheptene-3,7-di-yl

)bis-2-propenylchloride,
 3,7-bis(1,1-dimethylethyl)-10,11-dihydro-1,9-dimethyl-5H-d
 ibenzo[a,d]cycloheptene,
 2,8-bis(1,1-dimethylethyl)-10,11-dihydro-4,6-bis[2,4,6-tr
 5 imethylphenyl)methyl]-5H-dibenzo[a,d]cycloheptene,
 3,7-bis(chloromethyl)-10,11-dihydro-5H-dibenzo[a,d]cycloh
 eptene,
 3,7-bis(1,1-dimethylethyl)-10,11-dihydro-5H-dibenzo[a,d]c
 ycloheptene,
 10 4,6-bis(chloromethyl)-2,8-bis(1,1-dimethylethyl)-10,11-di
 hydro-5H-dibenzo[a,d]cycloheptene,
 10,11-dihydro-5H-dibenzo[a,d]cycloheptene-3-ol,
 3-chloro-10,11-dihydro-5H-dibenzo[a,d]cycloheptene,
 4,6-bis(chloromethyl)-10,11-dihydro-2,8-dimethoxy-1,3,7,9
 15 -tetramethyl)-5H-dibenzo[a,d]cycloheptene,
 10,11-dihydro-1-methyl-5H-dibenzo[a,d]cycloheptene,
 3,7-bis(1,1-dimethylethyl)-10,11-dihydro-1,9-dimethoxy-5H
 -dibenzo[a,d]cycloheptene,
 3,7-bis(1,1-dimethylethyl)-10,11-dihydro-1,9-bis(phenylme
 20 thyl)-5H-dibenzo[a,d]cycloheptene,
 10,11-dihydro-1,9-dimethyl-5H-dibenzo[a,d]cycloheptene,
 10,11-dihydro-3-methyl-5H-dibenzo[a,d]cycloheptene,
 1-(chloromethyl)-3,7-bis(1,1-dimethylethyl)-10,11-dihydro
 -5H-dibenzo[a,d]cycloheptene,
 25 2,8-bis(1,1-dimethylethyl)-10,11-dihydro-4-methyl-5H-dibe
 nzo[a,d]cycloheptene,
 10,11-dihydro-4-methyl-5H-dibenzo[a,d]cycloheptene,
 10,11-dihydro-3-(trifluoromethyl)-5H-dibenzo[a,d]cyclohep

tene,

10,11-dihydro-5H-dibenzo[a,d]cycloheptene-2-acetic acid,

4-(chloromethyl)-10,11-dihydro-2,8-dimethoxy-1,3,7,9-tetramethyl)-5H-dibenzo[a,d]cycloheptene,

5 1,9-bis(chloromethyl)-10,11-dihydro-3,7-dimethoxy-2,4,6,8-tetramethyl)-5H-dibenzo[a,d]cycloheptene,

10,11-dihydro-1-(phenylmethyl)-5H-dibenzo[a,d]cycloheptene,

10,11-dihydro-1,9-bis(phenylmethyl)-5H-dibenzo[a,d]cycloheptene,

10 10,11-dihydro-3,7-dimethyl-5H-dibenzo[a,d]cycloheptene,

1,9-bis(chloromethyl)-3,7-bis(1,1-dimethylethyl)-10,11-dihydro-5H-dibenzo[a,d]cycloheptene,

2,8-bis(1,1-dimethylethyl)-10,11-dihydro-4,6-dimethyl-5H-dibenzo[a,d]cycloheptene,

15 10,11-dihydro-2-methyl-5H-dibenzo[a,d]cycloheptene,

10,11-dihydro-2,3-dimethyl-5H-dibenzo[a,d]cycloheptene,

2,8-bis(1,1-dimethylethyl)-10,11-dihydro-5H-dibenzo[a,d]cycloheptene,

20 10,11-dihydro-5H-dibenzo[a,d]cycloheptene-2-ol,

6-(chloromethyl)-10,11-dihydro-2,8-dimethoxy-1,3,7,9-tetramethyl)-5H-dibenzo[a,d]cycloheptene,

10,11-dihydro-2,3,7,8-tetramethoxy-5H-dibenzo[a,d]cycloheptene,

25 3,7-bis(1,1-dimethylethyl)-10,11-dihydro-1-(phenylmethyl)-5H-dibenzo[a,d]cycloheptene,

2,8-bis(1,1-dimethylethyl)-

4,6-bis[(2,5-dimethylphenyl)methyl]-10,11-dihydro-5H-dibe

nzo[a,d]cycloheptene,

3,7-bis(1,1-dimethylethyl)-10,11-dihydro-1-methyl-5H-dibe

nzo[a,d]cycloheptene,

3-(chloromethyl)-10,11-dihydro-5H-dibenzo[a,d]cyclohepten

5 e,

10,11-dihydro-4,6-dimethyl-5H-dibenzo[a,d]cycloheptene,

and

4-(chloromethyl)-2,8-bis(1,1-dimethylethyl)-10,11-dihydro

-5H-dibenzo[a,d]cycloheptene.

10 Content of the Compound (I) in the polybutadiene
composition of the present invention is usually 0.01 part by
weight or more, preferably 0.01 part by weight or more, based
on 100 parts by weight of the polybutadiene composition. When
the content of Compound (I) is less than 0.01 part by weight,
15 thermal degradation cannot be prevented sufficiently. There
is no specific upper limit of the content of Compound (I).
However, from economical view point, it is usually 10 part
by weight or less, preferably 5 part by weight or less.

 The polybutadiene composition of the present invention
20 may optionally comprise an antioxidant such as phenol
antioxidants, sulfur antioxidants and phosphorous
antioxidant.

 Examples of the phenol antioxidant include

(1) alkylated monophenols, such as

25 2,6-di-t-butyl-4-methylphenol, 2,4,6-tri-t-butylphenol,
2,6-di-t-butylphenol, 2-t-butyl-4,6-dimethylphenol,
2,6-di-t-butyl-4-ethylphenol,
2,6-di-t-butyl-4-n-butylphenol,

- 2,6-di-t-butyl-4-isobutylphenol,
2,6-dicyclopentyl-4-methylphenol, 2-(α -methylcyclohexyl)-4,6-dimethylphenol,
2,6-dioctadecyl-4-methylphenol, 2,4,6-tricyclohexylphenol,
5 2,6-di-t-butyl-4-methoxymethylphenol,
2,6-di-nonyl-4-methylphenol,
2,4-dimethyl-6-(1'-methylundecyl-1'-yl)phenol,
2,4-dimethyl-6'-(1'-methylheptadecyl-1'-yl)phenol,
2,4-dimethyl-6-(1'-methyltridecyl-1'-yl)phenol and a
10 mixture thereof;
(2) alkylthiomethylphenols such as
2,4-dioctylthiomethyl-6-t-butylphenol,
2,4-dioctylthiomethyl-6-methylphenol,
2,4-dioctylthiomethyl-6-ethylphenol,
15 2,6-didodecylthiomethyl-4-nonylphenol and a mixture thereof;
(3) hydroquinones and alkylated hydroquinones such as
2,6-di-t-butyl-4-methoxyphenol, 2,5-di-t-butylhydroquinone,
2,5-di-t-amylhydroquinone,
2,6-diphenyl-4-octadecyloxyphenol,
20 2,6-di-t-butylhydroquinone,
2,5-di-t-butyl-4-hydroxyanisole,
3,5-di-t-butyl-4-hydroxyphenyl stearate,
bis(3,5-di-t-butyl-4-hydroxyphenyl)adipate and a mixture
thereof;
25 (4) tocopherols such as
 α -tocopherol, β -tocopherol, γ -tocopherol, δ -tocopherol
and a mixture thereof;
(5) hydroxylated thiodiphenyl ethers such as

2,2'-thiobis(6-t-butylphenol),
 2,2'-thiobis(4-methyl-6-t-butylphenol),
 2,2'-thiobis(4-octylphenol),
 4,4'-thiobis(3-methyl-6-t-butylphenol),
 5 4,4'-thiobis(2-methyl-6-t-butylphenol),
 4,4'-thiobis(3,6-di-t-amylphenol),
 4,4'-(2,6-dimethyl-4-hydroxyphenyl)disulfide and the like;
 (6) alkylidenebisphenols and derivative thereof such as
 2,2'-methylenebis(4-methyl-6-t-butylphenol),
 10 2,2'-methylenebis(4-ethyl-6-t-butylphenol),
 2,2'-methylenebis[4-methyl-6-(α -methylcyclohexyl)phenol]],
 2,2'-methylenebis(4-methyl-6-cyclohexylphenol),
 2,2'-methylenebis(4-methyl-6-nonylphenol),
 15 2,2'-methylenebis(4,6-di-t-butylphenol)],
 2,2'-ethylidenebis(4,6-di-t-butylphenol),
 2,2'-ethylidenebis(4-isobutyl-6-t-butylphenol),
 2,2'-methylenebis[6-(α -methylbenzyl)-4-nonylphenol],
 2,2'-methylenebis[6-(α , α -dimethylbenzyl)-4-nonylphenol],
 20 4,4'-methylenebis(6-t-butyl-2-methylphenol),
 4,4'-methylenebis(2,6-di-t-butylphenol),
 4,4'-butylidenebis(3-methyl-6-t-butylphenol),
 1,1-bis(4-hydroxyphenyl)cyclohexane,
 1,1-bis(5-t-butyl-4-hydroxy-2-methylphenyl)butane,
 25 2,6-bis[3-t-butyl-5-methyl-2-hydroxybenzyl]-4-methylpheno
 1, 1,1,3-tris(5-t-butyl-4-hydroxy-2-methylphenyl)butane,
 1,1-bis(5-t-butyl-4-hydroxy-2-methylphenyl)-3-n-dodecylme
 rcaptobutane,

bis[3,3-bis-3'-t-butyl-4'-hydroxyphenyl]butyrate],
 bis(3-t-butyl-4-hydroxy-5-methylphenyl)dicyclopentadiene,
 bis[2-(3'-t-butyl-2'-hydroxy-5'-methylbenzyl)-6-t-butyl-4-
 -methylphenyl]terephthalate,
 5 1,1-bis(3,5-dimethyl-2-hydroxyphenyl)butane,
 2,2-bis(3,5-di-t-butyl-4-hydroxyphenyl)propane,
 2,2-bis(5-t-butyl-4-hydroxy-2-methylphenyl)-4-n-dodecylme
 rcaptobutane,
 1,1,5,5-tetra(5-t-butyl-4-hydroxy-2-methylphenyl)pentane,
 10 2-t-butyl-6-(3'-t-butyl-5'-methyl-2'-hydroxybenzyl)-4-met
 hylphenyl acrylate,
 2,4-di-t-pentyl-6-[1-(2-hydroxy-3,5-di-t-pentylphenyl)eth
 yl]phenyl acrylate and a mixture thereof;
 (7) O-, N- and S-benzyl derivatives such as
 15 3,5,3',5'-tetra-t-butyl-4,4'-dihydroxydibenzyl ether,
 octadodecyl-4-hydroxy-3,5-dimethylbenzylmercapto acetate,
 tris(3,5-di-t-butyl-4-hydroxybenzyl)amine,
 bis(4-t-butyl-3-hydroxy-2,6-dimethylbenzyl)dithioterephth
 alate, bis(3,5-di-t-butyl-4-hydroxybenzyl)sulfide,
 20 isooctyl-3,5-di-t-butyl-4-hydroxybenzylmercapto acetate
 and a mixture thereof;
 (8) hydroxybenzylated malonate derivatives such as
 dioctadecyl-2,2-bis(3,5-di-t-butyl-2-hydroxybenzyl)malona
 te,
 25 dioctadecyl-2-(3-t-butyl-4-hydroxy-5-methylbenzyl)malonat
 e,
 didodecylmercaptoethyl-2,2-bis(3,5-di-t-butyl-4-hydroxybe
 nzyl)malonate,

bis[4-(1,1,3,3-tetramethylbutyl)phenyl]-2,2-bis(3,5-di-t-butyl-4-hydroxybenzyl)malonate and a mixture thereof;

(9) aromatic hydroxybenzyl derivatives such as

1,3,5-trimethyl-2,4,6-tris(3,5-di-t-butyl-4-hydroxybenzyl)
5)benzene,

1,4-bis(3,5-di-t-butyl-4-hydroxybenzyl)-2,3,5,6-tetramethylbenzene, 2,4,6-tris(3,5-t-butyl-4-hydroxybenzyl)phenol and a mixture thereof;

(10) triazine derivatives

10 2,4-bis(n-octylthio)-6-(4-hydroxy-3,5-di-t-butylanilino)-1,3,5-triazine,

2-n-octylthio-4,6-bis(4-hydroxy-3,5-di-t-butylanilino)-1,3,5-triazine,

15 2-n-octylthio-4,6-bis(4-hydroxy-3,5-di-t-butylphenoxy)-1,3,5-triazine,

2,4,6-tris(3,5-di-t-butyl-4-hydroxy)-1,3,5-triazine,

tris(4-t-butyl-3-hydroxy-2,6-dimethylbenzyl isocyanurate,

tris(3,5-di-t-butyl-4-hydroxybenzyl)isocyanurate,

20 2,4,6-tris(3,5-di-t-butyl-4-hydroxyphenylethyl)-1,3,5-triazine,

2,4,6-tris(3,5-di-t-butyl-4-hydroxyphenylpropyl)-1,3,5-triazine, tris(3,5-dicyclohexyl-4-hydroxybenzyl)isocyanurate,

tris[2-(3',5'-di-t-butyl-4'-hydroxycinnamoyloxy)ethyl]isocyanurate and a mixture thereof;

25 (11) benzyl phosphonate derivatives such as

dimethyl-3,5-di-t-butyl-4-hydroxybenzyl phosphonate,

diethyl-3,5-di-t-butyl-4-hydroxybenzyl phosphonate,

dioctadecyl-3,5-di-t-butyl-4-hydroxybenzyl phosphonate,

dioctadecyl-5-t-butyl-4-hydroxy-3-methylbenzyl phosphonate, calcium salt of 3,5-di-t-butyl-4-hydroxybenzyl phosphonic acid monoester and a mixture thereof;

(12) acylaminophenol derivatives such as

5 anilide 4-hydroxylaurate, anilide 4-hydroxystearate, octyl-N-(3,5-di-t-butyl-4-hydroxyphenyl)carbanate and a mixture thereof;

(13) esters of β -(3,5-di-t-butyl-4-hydroxyphenyl)propionic acid and the following monohydric or polyhydric alcohol:

10 methanol, ethanol, octanol, octadecanol, ethylene glycol, 1,3-propanediol, 1,4-butanediol, 1,6-hexanediol, 1,9-nonanediol, neopentyl glycol, diethylene glycol, thioethylene glycol, spiro glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate,
15 N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2,2,2]octane and a mixture thereof;

20 (14) esters of β -(5-t-butyl-4-hydroxy-3-methylphenyl)propionic acid and the following monohydric or polyhydric alcohol:

methanol, ethanol, octanol, octadecanol, ethylene glycol, 1,3-propanediol, 1,4-butanediol, 1,6-hexanediol,
25 1,9-nonanediol, neopentyl glycol, diethylene glycol, thioethylene glycol, spiro glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol,

3-thiapentadecanol, trimethylhexanediol,
trimethylolpropane,
4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2,2,2]octan
e and a mixture thereof;

- 5 (15) esters of β -(3,5-dicyclohexyl-4-hydroxyphenyl)
propionic acid and the following monohydric or polyhydric
alcohol:

methanol, ethanol, octanol, octadecanol, ethylene glycol,
1,3-propanediol, 1,4-butanediol, 1,6-hexanediol,

- 10 1,9-nonanediol, neopentyl glycol, diethylene glycol,
thioethylene glycol, spiro glycol, triethylene glycol,
pentaerythritol, tris(hydroxyethyl)isocyanurate,
N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol,
3-thiapentadecanol, trimethylhexanediol,

- 15 trimethylolpropane,
4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2,2,2]octan
e and a mixture thereof;

(16) esters of 3,5-di-t-butyl-4-hydroxyphenylacetic acid and
the following monohydric or polyhydric alcohol:

- 20 methanol, ethanol, octanol, octadecanol, ethylene glycol,
1,3-propanediol, 1,4-butanediol, 1,6-hexanediol,
1,9-nonanediol, neopentyl glycol, diethylene glycol,
thioethylene glycol, spiro glycol, triethylene glycol,
pentaerythritol, tris(hydroxyethyl)isocyanurate,

- 25 N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol,
3-thiapentadecanol, trimethylhexanediol,
trimethylolpropane,
4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2,2,2]octan

e and a mixture thereof; and

(17) amides of β -(3,5-di-t-butyl-4-hydroxyphenyl)propionic acid such as

N,N'-bis[3-(3',5'-di-t-butyl-4'-hydroxyphenyl) propionyl]

5 hydrazine,

N,N'-bis[3-(3',5'-di-t-butyl-4'-hydroxyphenyl)propionyl]h
examethylenediamine,

N,N'-bis[3-(3',5'-di-t-butyl-4'-hydroxyphenyl)propionyl]
trimethylenediamine and a mixture thereof.

10 Phenol antioxidants such as those mentioned above can
be used singly or as a combination of two or more of them.

Examples of the phosphorous antioxidant include:

triphenyl phosphite, tris(nonylphenyl)phosphite,
tris(2,4-di-t-butylphenyl)phosphite, trilauryl phosphite,
15 trioctadecyl phosphite, distearyl pentaerythritol
diphosphite, diisodecyl pentaerythritol diphosphite,
bis(2,4-di-t-butylphenyl)pentaerythritol diphosphite,
bis(2,4-di-t-butyl-6-methylphenyl)pentaerythritol
diphosphite,

20 bis(2,4-di-t-butyl-6-methylphenyl)pentaerythritol
diphosphite,

bis(2,6-di-t-butyl-4-methylphenyl)pentaerythritol
diphosphite, bis(2,4,6-tri-t-butylphenyl)pentaerythritol
diphosphate, tristearyl sorbitol triphosphite,

25 tetrakis(2,4-di-t-butylphenyl)-4,4'-diphenylene
diphosphite,

2,2'-methylenebis(4,6-di-t-butylphenyl)2-ethylhexyl
phosphite, 2,2'-ethylidenebis(4,6-di-t-butylphenyl)fluoro

phosphite, bis(2,4-di-t-butyl-6-methylphenyl)ethyl
phosphite, bis(2,4-di-t-butyl-6-methylphenyl)methyl
phosphite,
(2,4,6-tri-t-butylphenyl)-5-ethyl-5-butyl-1,3,2-oxaphosph
5 orinane,
2,2',2''-nitrilo[triethyl-tris(3,3',5,5'-tetra-t-butyl-1,1
'-biphenyl-2,2'-diyl)phosphite and a mixture thereof.

Phosphorous antioxidants such as those mentioned above
can be used singly or as a combination of two or more of them.

10 Examples of the sulfur antioxidant include:

dilauryl 3,3'-thiodipropionate, tridecyl
3,3'-thiodipropionate, dimyristyl 3,3'-thiodipropionate,
distearyl 3,3'-thiodipropionate, lauryl stearyl
3,3'-thiodipropionate, neopentanetetraylkis(3-lauryl
15 thiopropionate) and a mixture thereof.

Sulfur antioxidants such as those mentioned above can
be used singly or as a combination of two or more of them.

Usually, an antioxidant such as those mentioned above
is comprised in an amount of 0.001 part by weight or more in
20 the polybutadiene composition of the present invention based
on 100 parts by weight of the polybutadiene composition. From
economical view point, its amount is usually 10 part by weight
or less based on 100 parts by weight of the polybutadiene
composition.

25 The polybutadiene composition of the present invention
may further comprise other additives such as ultraviolet
absorber, photostabilizer, hydroxylamine, metal inactivating
agent, lubricant, metal soap, nucleating agent, antistatic

agent, flame retardant, pigment, filler and the like.

Examples of the ultraviolet absorbers include

(1) salicylate derivatives such as

phenyl salicylate, 4-t-butylphenyl salicylate,

5 2,4-di-t-butylphenyl 3',5'-di-t-butyl-4'-hydroxybenzoate,

4-t-octylphenyl salicylate,

bis(4-t-butylbenzoyl)resorcinol, benzoylresorcinol,

hexadecyl 3',5'-di-t-butyl-4'-hydroxybenzoate, octadecyl

3',5'-di-t-butyl-4'-hydroxybenzoate,

10 2-methyl-4,6-di-t-butylphenyl

3',5'-di-t-butyl-4'-hydroxybenzoate and a mixture thereof;

(2) 2-hydroxybenzophenone derivatives such as

2,4-dihydroxybenzophenone, 2-hydroxy-4-methoxybenzophenone,

2-hydroxy-4-octoxybenzophenone,

15 2,2'-dihydroxy-4-methoxybenzophenone,

bis(5-benzoyl-4-hydroxy-2-methoxyphenyl)methane,

2,2',4,4'-tetrahydroxybenzophenone and a mixture thereof; and

(3) 2-(2'-hydroxyphenyl)benzotriazoles such as

2-(2-hydroxy-5-methylphenyl)benzotriazole,

20 2-(3',5'-di-t-butyl-2'-hydroxyphenyl)benzotriazole,

2-(5'-t-butyl-2'-hydroxyphenyl)benzotriazole,

2-(2'-hydroxy-5'-t-octylphenyl)benzotriazole,

2-(3-t-butyl-2-hydroxy-5-methylphenyl)-5-chlorobenzotriazole,

25 2-(3'-s-butyl-2'-hydroxy-5'-t-butylphenyl)benzotriazole,

2-(2'-hydroxy-4'-octyloxyphenyl)benzotriazole,

2-(3',5'-di-t-amyl-2'-hydroxyphenyl)benzotriazole,

2-[2'-hydroxy-3',5'-bis(α , α

-dimethylbenzyl)phenyl]-2H-benzotriazole,
 2-[(3'-t-butyl-2'-hydroxyphenyl)-5'-(2-octyloxycarbonyl-
 ethyl)phenyl]-5-
 chlorobenzotriazole,
 5 2-[3'-t-butyl-5'-[2-(2-ethylhexyloxy)carbonyl-ethyl]-2'-hydroxyphenyl]-5-chlorobenzotriazole,
 2-[3'-t-butyl-2'-hydroxy-5'-(2-methoxycarbonyl-ethyl)phenyl]-5-chlorobenzotriazole,
 2-[3'-t-butyl-2'-hydroxy-5'-(2-methoxycarbonyl-ethyl)phenyl]benzotriazole,
 10 2-[3'-t-butyl-2'-hydroxy-5-(2-octyloxycarbonyl-ethyl)phenyl]benzotriazole,
 2-[3'-t-butyl-2'-hydroxy-5'-[2-(2-ethylhexyloxy)carbonyl-ethyl]phenyl]benzotriazole,
 15 2-[2-hydroxy-3-(3,4,5,6-tetrahydrophthalimide-methyl)-5-methylphenyl]benzotriazole,
 2-(3',5'-di-t-butyl-2-hydroxyphenyl)-5-chlorobenzotriazole, mixture of
 20 2-(3'-dodecyl-2'-hydroxy-5'-methylphenyl)benzotriazole and
 2-[3'-t-butyl-2'-hydroxy-5'-(2-isooctyloxycarbonyl-ethyl)phenyl]benzotriazole,
 2,2'-methylenebis[6-(2H-benzotriazol-2-yl)-4-(1,1,3,3-tetramethylbutyl)phenol],
 25 2,2'-methylenebis[4-t-butyl-6-(2H-benzotriazol-2-yl)phenol], condensate of poly(3-11)(ethylene glycol) and
 2-[3'-t-butyl-2'-hydroxy-5'-(2-methoxycarbonyl-ethyl)phenyl]benzotriazole, condensate of poly(3-11)(ethylene glycol)

and methyl

3-[3-(2H-benzotriazol-2-yl)-5-t-butyl-4-hydroxyphenyl]propionate, 2-ethylhexyl

3-[3-t-butyl-5-(5-chloro-2H-benzotriazol-2-yl)-4-hydroxyphenyl]propionate, octyl

3-[3-t-butyl-5-(5-chloro-2H-benzotriazol-2-yl)-4-hydroxyphenyl]propionate, methyl

3-[3-t-butyl-5-(5-chloro-2H-benzotriazol-2-yl)-4-hydroxyphenyl]propionate,

3-[3-t-butyl-5-(5-chloro-2H-benzotriazol-2-yl)-4-hydroxyphenyl]propionic acid and a mixture thereof.

The ultraviolet absorbers such as those mentioned above can be used singly or as a combination of two or more of them.

Examples of the photo stabilizer include

(1) hindered amine photo stabilizers such as
bis(2,2,6,6-tetramethyl-4-piperidyl)sebacate,
bis(2,2,6,6-tetramethyl-4-piperidyl)succinate,
bis(1,2,2,6,6-pentamethyl-4-piperidyl)sebacate,
bis(N-octoxy-2,2,6,6-tetramethyl-4-piperidyl)sebacate,
bis(N-benzyloxy-2,2,6,6-tetramethyl-4-piperidyl)sebacate,
bis(N-cyclohexyloxy-2,2,6,6-tetramethyl-4-piperidyl)sebacate,
bis(1,2,2,6,6-pentamethyl-4-piperidyl)
2-(3,5-di-t-butyl-4-hydroxybenzyl)-2-butylmalonate,
bis(1-acrolyl-2,2,6,6-tetramethyl-4-piperidyl)
2,2-bis(3,5-di-t-butyl-4-hydroxybenzyl)-2-butylmalonate,
bis(1,2,2,6,6-pentamethyl-4-piperidyl) decanedioate,
2,2,6,6-tetramethyl-4-piperidyl methacrylate,

4-[3-(3,5-di-t-butyl-4-hydroxyphenyl)propionyloxy]-1-[2-(
 3-(3,5-di-t-butyl-4-hydroxyphenyl)propionyloxy)ethyl]-2,2
 ,6,6-tetramethylpiperidine,
 2-methyl-2-(2,2,6,6-tetramethyl-4-piperidyl)amino-N-(2,2,
 5 6,6-tetramethyl-4-piperidyl)propionamide,
 tetarkis(2,2,6,6-tetramethyl-4-piperidyl)
 1,2,3,4-butaneteracarboxylate,
 tetrakis(1,2,2,6,6-pentamethyl-4-piperidyl)
 1,2,3,4-butanetetracarboxylate, mixed esterified product of
 10 1,2,3,4-butanetetracarboxylic acid and
 1,2,2,6,6-pentamethyl-4-piperidinol and 1-tridecanol, mixed
 esterified product of 1,2,3,4-butanetetracarboxylic acid and
 2,2,6,6-tetramethyl-4-piperidinol and 1-tridecanol, mixed
 esterified product of 1,2,3,4-butanetetracarboxylic acid and
 15 1,2,2,6,6-pentamethyl-4-piperidinol and
 3,9-bis(2-hydroxy-1,1-dimethylethyl)-2,4,8,10-tetraoxaspi
 ro[5.5]undecane,
 mixed esterified product of 1,2,3,4-butanetetracarboxylic
 acid and 2,2,6,6-tetarmethyl-4-piperidinol and
 20 3,9-bis(2-hydroxy-1,1-dimethylethyl)-2,4,8,10-tetraoxaspi
 ro[5.5]undecane, polycondensate of dimethyl succinate and
 1-(2-hydroxyethyl)-4-hydroxy-2,2,6,6-tetramethylpiperidin
 e,
 poly[(6-morpholino-1,3,5-triazin-2,4-diyl)((2,2,6,6-tetra
 25 methyl-4-piperidyl)imino)hexamethylene
 ((2,2,6,6-tetramethyl-4-piperidyl)imino)],
 poly[(6-(1,1,3,3-tetramethylbutyl)imino-1,3,5-triazin-2,4
 -diyl

((2,2,6,6-tetramethyl-4-piperidyl)imino)hexamethylene
((2,2,6,6-tetramethyl-4-piperidyl)imino)), polycondensate
of

N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenedia
mine and 1,2-bromoethane,

N,N',4,7-tetrakis[4,6-bis(N-butyl-N-(2,2,6,6-tetramethyl-
4-piperidyl)amino)-1,3,5-triazin-2-yl]-4,7-diazadecane-1,
10 diamine,

N,N',4-tris[4,6-bis(N-butyl-N-(2,2,6,6-tetramethyl-4-pipe
ridyl)amino)-1,3,5-triazin-2-yl]-4,7-diazadecane-1,10
diamine,

N,N',4,7-tetrakis[4,6-bis(N-butyl-N-(1,2,2,6,6-pentamethy
l-4-piperidyl)amino)-1,3,5-triazin-2-yl]-4,7-diazadecane-
1,10 diamine,

N,N',4-tris[4,6-bis(N-butyl-N-(1,2,2,6,6-pentamethyl-4-pi
peridyl)amino)-1,3,5-triazin-2-yl]-4,7-diazadecane-1,10
diamine and a mixture thereof;

(2) acrylate photo stabilizers such as

ethyl α -cyano- β , β -diphenylacrylate, isooctyl α -cyano- β ,
 β -diphenylacrylate, methyl α -carbomethoxycinnamate, methyl
 α -cyano- β -methyl-methoxycinnamate, butyl α -cyano- β
-methyl-p-methoxycinnamate, methyl α
-carbomethoxy-p-methoxycinnamate, N-(β -carbomethoxy- β
-cyanovinyl)-2-methylindoline and a mixture thereof;

(3) nickel photo stabilizers such as

nickel complex of

2,2'-thiobis-[4-(1,1,3,3-tetramethylbutyl)phenol], nickel
dibutyldithiocarbamate, nickel salt of monoalkyl ester,

nickel complex of ketoxime and a mixture thereof;

(4) oxamide photo stabilizers such as

4,4'-dioctyloxyoxanilide, 2,2'-diethoxyoxanilide,

2,2'-dioctyloxy-5,5'-di-t-butylanilide,

5 2,2'-didodecyloxy-5,5'-di-t-butylanilide,

2-ethoxy-2'-ethyloxanilide,

N,N'-bis(3-dimethylaminopropyl)oxamide,

2-ethoxy-5-t-butyl-2'-ethoxyanilide,

2-ethoxy-5,4'-di-t-butyl-2'-ethyloxanilide and a mixture

10 thereof; and

(5) 2-(2-hydroxyphenyl)-1,3,5-triazine photo stabilizers
such as

2,4,6-tris(2-hydroxy-4-octyloxyphenyl)-1,3,5-triazine,

2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(2,4-dimethylphenyl

15)-1,3,5-triazine,

2-(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-
-triazine,

2,4-bis(2-hydroxy-4-propyloxyphenyl)-6-(2,4-dimethylpheny
1)-1,3,5-triazine,

20 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,
3,5-triazine,

2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(4-methylphenyl)-
1,3,5-triazine,

2-[2-hydroxy-4-(2-hydroxy-3-butyloxypropoxy)phenyl]-4,6-b
25 is(2,4-dimethylphenyl)-1,3,5-triazine,

2-[2-hydroxy-4-(2-hydroxy-3-octyloxypropoxy)phenyl]4,6-bi
s(2,4-dimethylphenyl)-1,3,5-triazine and a mixture thereof.

Examples of the hydroxyamine include

N,N-dibenzylhydroxyamine, N,N-diethylhydroxyamine,
N,N-dioctylhydroxyamine, N,N-dilaurylhydroxyamine,
N,N-ditetradecylhydroxyamine, N,N-dihexadecylhydroxyamine,
N,N-dioctadecylhydroxyamine, N,N-dibenzylhydroxyamine,
5 N,N-dibenzylhydroxyamine,
N-hexadecyl-N-octadecylhydroxyamine,
N-heptadecyl-N-octadecylhydroxyamine and a mixture thereof.

Examples of the metal inactivating agent include
N,N'-diphenyloxamide, N-salicylal-N'-salicyloylhydrazine,
10 N,N'-bis(salicyloyl)hydrazine,
N,N'-bis(3,5-di-t-butyl-4-hydroxyphenylpropionyl)hydrazin
e, 3-salicyloylamino-1,2,4-triazole,
bis(benzylidene)oxalyl dihydrazide, oxalinide, isophthaloyl
dihydrazide, sebacoylbisphenyl hydrazide,
15 N,N'-bis(salicyloyl)thiopropionyl dihydrazide and a mixture
thereof.

Examples of the lubricant include aliphatic hydrocarbon
such as paraffin or wax, higher aliphatic acid having 8 to
22 carbon atoms, higher aliphatic acid (having 8 to 22 carbon
20 atoms) metal (Al, Ca, Mg, Zn) salt, aliphatic alcohol having
8 to 22 carbon atoms, polyglycol, ester of higher fatty acid
having 4 to 22 carbon atoms and aliphatic monohydric alcohol
having 4 to 18 carbon atoms, higher aliphatic amide having
8 to 22 carbon atoms, silicone oil, rosin derivative and the
25 like.

The polybutadiene composition of the present invention
can be produced, for example, by melt-kneading a polybutadiene
type polymer and Compound (I). More specifically saying, it

can be produced by adding Compound (I) to a melt-kneaded polybutadiene type polymer, followed by melt-kneading, further. Alternatively, the Compound (I) can be added while the polymerization reaction for producing the polybutadiene type polymer is proceeding or immediately after the end of the polymerization reaction. The Compound (I) may be added as a solid state or as a solution where it was dissolved in a solvent.

When an antioxidant and/or another additive are added to the composition, the Compound (I) may also be added at the same time. When they are added at the same time, the Compound (I) may be dissolved in a heat-melted antioxidant and/or other additive. If the antioxidant and/or other additive are in liquid state, the Compound (I) may be dissolved or dispersed in them.

The Compound (I) prevents thermal degradation of a polybutadiene type polymer, and stabilizes said polymer. Accordingly, incorporating the Compound (I) in a polybutadiene type polymer is a effective method for stabilizing the polybutadiene type polymer. In the stabilizing method, the amount of Compound (I) to be incorporated in the polybutadiene composition is usually 0.01 part by weight or more, preferably 0.05 part by weight or more, and usually 10 parts by weight or less, preferably 5 parts by weight or less.

The Compound (I) is useful as a stabilizer for a polybutadiene type polymer to suppress thermal degradation of the polymer. The stabilizer may optionally comprise an antioxidant or another additive in addition to the Compound

(I).

As explained above, in the polybutadiene composition, thermal degradation of the polybutadiene type polymer is suppressed. As the result, generation of crosslinked matter
5 in various molded articles, such as hoses, footwear, toys, films and various vessels, which are obtained by injection molding, extrusion, blow molding or the like, can be reduced, if the molded articles are produced from the polybutadiene composition of the present invention.

10 In the polybutadiene composition of the present invention, thermal degradation of the polybutadiene type polymer can be prevented even in an air-free environment.

The present invention will be explained in more detail with the following examples, which should not be construed
15 to limit the scope of the invention. In the examples, parts is weight basis unless otherwise stated.

Examples 1-6

To 100 parts of styrene-butadiene block copolymer
20 [melt-flow rate: 13.3 g/10 minutes], 0.1 part of each of the compounds 1-6 listed below was added as the Compound (I), and the mixture was melt-kneaded at 200 °C with 30 mm ϕ mono-axial extruder to obtain pellets of the polybutadiene composition.

compound 1: anthracene

25 compound 2: 10,11-dihydro-5H-dibenzo[a,d]cycloheptene

compound 3: xanthene

compound 4: xanthone (9-xanthenon)

compound 5: anthraquinone

compound 6: anthrone

Melt flow rate of the pellets was measured with a melt indexer [L246-2531, manufactured by Techno Seven Co.] at the holding time of 15 minutes, at the temperature of 245 °C, and at the load of 2160 g. The results are shown in Table 1. The smaller melt flow rate at the holding time of 15 minutes indicates the less thermal degradation and cross-linked matter.

Comparative example 1

According to the same procedure as in Examples 1-6 except that 0.1 part of the Compound (I) was not added, pellets were obtained, and melt flow rate at the holding time of 15 minutes was measured. The results are shown in Table 1.

Table 1

Compound (I)	Example No.						Comparative Example 1
	1	2	3	4	5	6	
Amount of the Compound (I)*							
Compound 1	0.1	-	-	-	-	-	-
Compound 2	-	0.1	-	-	-	-	-
Compound 3	-	-	0.1	-	-	-	-
Compound 4	-	-	-	0.1	-	-	-
Compound 5	-	-	-	-	0.1	-	-
Compound 6	-	-	-	-	-	0.1	-
MFR (g/10minutes)	39	34	39	35	34	38	4

* parts per 100 parts of the composition

Examples 7-9

To 100 parts of
acrylonitrile-butadiene-styrene-butadiene copolymer
[melt-flow rate: 13.3 g/10 minutes], 0.1 part of each of the
compounds 1, 3 and 6 listed below was added as the Compound
5 (I), and the mixture was melt-kneaded at 240 °C with 30 mm
φ mono-axial extruder to obtain pellets of the polybutadiene
composition, which were then dried with hot air.

compound 1: anthracene

compound 3: xanthene

10 compound 6: anthrone

Immediately after the pellets thus obtained were heated
to 245 °C, molding was conducted with 5.50z injection molder
to obtain an Izod test bar having a thickness of 4 mm for impact
15 test. According to JISK 7110, impact resistance was measured.
The results are shown in Table 1 in the row "Izod before holding".

The same procedure as above was repeated except that the
molding was conducted not immediately after but after 15
minutes of melt-kneading at 245 °C in the same injection molder.
20 Then, according to JIS K 7110, impact resistance was measured,
and the results are shown in Table 1 in the row "Izod after
holding".

Comparative example 2

25 According to the same procedure as in Examples 7-9 except
that 0.1 part of the Compound (I) was not added, pellets were
obtained, and impact resistances before and after holding were
measured. The results are shown in Table 1 in the rows, "Izod

before holding" and "Izod after holding".

Table 2

Compound (I)	Example No.			Comparative Example 1
	1	2	3	
Amount of the Compound (I)				
Compound 1	0.1	-	-	-
Compound 2	-	0.1	-	-
Compound 3	-	-	0.1	-
Izod (Kg.cm.cm)				
Before holding	24.6	24.8	25.1	22.7
After holding	18.1	18.5	20.1	15.6